Amendments

Amendment to the Claims:

The listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Silanised, structurally modified silicas, characterised by vinyl groups or vinyl silyl groups fixed to the surface, hydrophobic groups such as trimethyl silyl and/or dimethyl silyl and/or monomethyl silyl additionally being fixed to the surface, having the following physicochemical properties:

BET surface area m^2/g : 25 - 400

Average primary

particle size nm: 5 - 50

pH: 3-10

Carbon content %: 0.1-10

DBP value %: < 200 or not determinable

- 2. (Currently amended) Process The process for producing the silanised, structurally modified silicas according to claim 1, characterised in that comprising treating silicas are treated with a surface-modifying agent to form a mixture, heat treating the mixture obtained is heat treated and then structurally modified.
- 3. (Currently amended) Process The process for producing the silanised, structurally modified silicas according to claim 2, characterised in that wherein the silica treating step includes spraying the silicas are sprayed first with water and then with the surface-modifying agent, optionally mixed further, then heat treated and then structurally modified.

- 4. (Currently amended) Process The process for producing the silanised, structurally modified silica according to claim 2, characterised in that wherein the silica treating step includes treating the silica is treated with the surface-modifying agent in vapour form, the mixture heat treated and then structurally modified.
- 5. (Currently amended) Process The process for producing the silanised, structurally modified silica according to claim 3, characterised in that further comprising post-grounding and/or conditioning the structurally modified silica is post-ground and/or conditioned.
- 6. (Currently amended) Process The process for producing the silanised, structurally modified silica according to claim 4, characterised in that further comprising grinding and/or conditioning the structurally modified silica is post ground and/or conditioned.
- 7. (Currently amended) A silicone rubber containing a filler wherein the improvement comprises Use of the silanised, structurally modified silica according to claim 1 as a the filler-in silicone rubber.
- 8. (New) The process according to claim 3 further comprising, prior to heat treatment step, further mixing the treated silica mixture.